




OLYMPIC-16



Olympic-16 kraft pulp is a blend of Northwest long fibers designed for consistently high strengths, bulk and uniformity.

Olympic-16 is used extensively in kraft applications where fast development qualities are desired along with the inherent strength values of northern softwood. This combination provides excellent results in kraft multiwall sack paper, as well as kraft paper specialties.

Olympic-16 is packaged in 500 pound bales.

Multiply vertical scale by:
 10 for Freeness
 100 for Breaking Length

Test figures represent typical values, not minimums. Tests are made according to TAPPI standard methods. Schopper-Riegler (°SR) scale is an estimate.

Freeness CSF	Burst Factor $\frac{g_f \cdot m^2}{g \cdot cm^2}$	Tear Factor $\frac{100g_f \cdot m^2}{g}$	Breaking Length m
700	20	215	4,000
600	58	120	8,400
500	67	101	9,700
400	71	99	10,000
300	73	98	10,200